

5.2 Guarantee Matrix – Aluminium Substrates – UK/Local

Environment	Interpon D System		
	Interpon D1036 Guarantee Period	Requirements ¹	Interpon D2525 Guarantee Period
Normal C3 Inland	30 years all finishes and gloss levels	Clean every 12 months	40 years all finishes and gloss levels
Marine - C4 Coastal	30 years all finishes and gloss levels	Minimum 60 microns Clean every 12 months	40 years all finishes and gloss levels
	30 years all finishes and gloss levels	Minimum 60 microns Clean every 6 months	40 years all finishes and gloss levels
Marine – C5	25 years all finishes and gloss levels	Minimum 60 microns Clean every 3 months	30 years all finishes and gloss levels
	Not available		Not available
Industrial – C4	30 years all finishes and gloss levels	Minimum 60 microns Clean every 12 months	40 years all finishes and gloss levels
	30 years all finishes and gloss levels	Minimum 60 microns Clean every 6 months	40 years all finishes and gloss levels
	25 years all finishes and gloss levels	Minimum 60 microns Clean every 3 months	25 years all finishes and gloss levels
Industrial - C5	Not available		Not available
Swimming Pools - CX	25 years all finishes and gloss levels	Minimum 60 microns Clean every 3 months	25 years all finishes and gloss levels
	Not available		Not available

Notes: Environmental classification as defined by ISO 12944-2-2018

¹ Refer to Interpon D Approved Applicator Manual for full explanation of requirements